



STATIKUS TÖMÍTŐZSINÓROK STATIC PACKINGS

A Temac által gyártott statikus tömítőzsinórok sütőajtók, tűzhelyek bojlerrek szigetelésénél használhatók alacsony nyomáson. 500°C-ig üvegszál, 1100°C-ig Inconel króm-acél huzallal erősített kerámiaszál használják. Egyedi igényre bazaltszál tömítőzsinór is elérhető, mely 750°C-ig hőálló. A zsinórok szögletes, háromszög és kör fonatban érhetők el. További méretek igény esetén rendelhetők.

Static packings produced by Temac are mostly used for sealing of oven doors, boilers, stoves. These materials are used under low pressure. For temperature up to 500°C glass yarn, while up to 1100°C ceramic yarn reinforced with Inconel chrome-steel wire is used. For special applications packings from basalt yarn is available for temperature up to 750°C. These sealings are made in square, rectangular and round shapes. Other dimensions are available upon request.

ISOTEM 10, ÜVEGSZÁLAS ISOTEM 10, GLASS YARN



Típus Type	Isotem 10
Hőállóság Temperature	max. 500°C
Szín Color	Fehér White
Tulajdonság Properties	Szögletes, fonott üvegszál Square braided glass yarn

Cikkszám Code	Méret Size	Kiszereles Quantity
	(mm)	(m)
63.509.001	6	200
63.509.002	8	100
63.509.003	10	100
63.509.004	12	50
63.509.005	14	50
63.509.006	15	50
63.509.007	16	50
63.509.008	18	50
63.509.009	20	25
63.509.010	25	25
63.509.011	30	25
63.509.012	35	25
63.509.013	40	10
63.509.014	45	10
63.509.015	50	10

ISOTEM 20, ÜVEGSZÁLAS
ISOTEM 20, GLASS YARN

Típus Type	Isotem 20
Hőállóság Temperature	max. 500°C
Szín Color	Fehér White
Tulajdonság Properties	Kör, fonott üvegszál Round braided glass yarn

Cikkszám Code	Méret Size	Kiszerezés Quantity
	(mm)	(m)
63.510.001	6	200
63.510.002	8	100
63.510.003	10	100
63.510.004	12	50
63.510.005	14	50
63.510.006	15	50
63.510.007	16	50
63.510.008	18	50
63.510.009	20	25
63.510.010	25	25
63.510.011	30	25
63.510.012	35	25
63.510.013	40	10
63.510.014	45	10
63.510.015	50	10

ISOTEM 50, KERÁMIASZÁLAS ISOTEM 50, CERAMIC YARN



Típus Type	Isotem 50 I	Isotem 50 G
Hőállóság Temperature	max. 1100°C	max. 650°C
Szín Color	Fehér White	
Tulajdonság Properties	Szögletes, fonott kerámiaszál Square braided ceramic yarn	
	Inconel erősítéssel with Inconel reinforcement	Üvegszál erősítéssel with Glass reinforcement

Cikkszám Code		Méret Size	Kiszereles Quantity
50I	50G	(mm)	(m)
63.507.001	62.002.001	6	200
63.507.002	62.002.002	8	200
63.507.003	62.002.003	10	100
63.507.004	62.002.004	12	100
63.507.005	62.002.005	14	50
63.507.006	62.002.006	15	50
63.507.007	62.002.007	16	50
63.507.008	62.002.008	18	50
63.507.009	62.002.009	20	25
63.507.010	62.002.010	25	25
63.507.011	62.002.011	30	25
63.507.012	62.002.012	35	25
63.507.013	62.002.013	40	10
63.507.014	62.002.014	45	10
63.507.015	62.002.015	50	10

ISOTEM 60, KERÁMIASZÁLAS ISOTEM 60, CERAMIC YARN



Típus Type	Isotem 60 I	Isotem 60 G
Hőállóság Temperature	max. 1100°C	max. 650°C
Szín Color	Fehér White	
Tulajdonság Properties	Kör, fonott kerámiaszál Round braided ceramic yarn	
	Inconel erősítéssel with Inconel reinforcement	Üvegszál erősítéssel with Glass reinforcement

Cikkszám Code		Méret Size	Kiszereles Quantity
60I	60G	(mm)	(m)
63.508.001	62.002.016	6	200
63.508.002	62.002.017	8	200
63.508.003	62.002.018	10	100
63.508.004	62.002.019	12	100
63.508.005	62.002.020	14	50
63.508.006	62.002.021	15	50
63.508.007	62.002.022	16	50
63.508.008	62.002.023	18	50
63.508.009	62.002.024	20	25
63.508.010	62.002.025	25	25
63.508.011	62.002.026	30	25
63.508.012	62.002.027	35	25
63.508.013	62.002.028	40	10
63.508.014	62.002.029	45	10
63.508.015	62.002.030	50	10